☐ Motive Battery









Energy Storage Battery-Tubular GEL Technology-OPzV Series

OPzV300

(2V 300Ah) **GENERAL FEATURES**

- 20 years design life at floating condition
- Wide operating temperature range from -40°C to +60°C
- Tubular positive plate with prolonged cycle life
- Fumed silica gel electrolyte
- lead-calcium grid significantly improves the corrosion resistance ability
- Low self-discharge rate and long shelf life
- Excellent deep discharge recovery capability


Application

- Renewable energy system
- Hybrid solar power system
- Uninterrupted Power Supply (UPS)
- Communications and electric equipment
- Emergency lighting equipment
- Fire alarm and security systems
- Control equipment, and other factory automation equipment
- Emergency power supply (EPS)
- Lighting equipment

Dimension

Unit:mm

Length 145±2mm / 5.71inch Width 206±2mm / 8.11inch Container Height 356±3mm / 14.02inch **Total Height** 389±3mm / 15.31inch




Unit:mm

Terminal Type:

Weight

26.5kg 58.42lbs











This document is subject to change without prior notification

Motive Battery





■ Reserve Battery

■ Motorcycle Battery

OPzV300

Specificaion						
Nominal Voltag	e	2V				
		318Ah 20hr Rate(1.80V/cell)				
		300Ah 10hr Rate(1.80V/cell)				
Rated Capacity(25°C)		262Ah 5hr Rate(1.75V/cell)				
		235Ah 3hr Rate(1.70V/cell)				
		179Ah 1hr Rate(1.60V/cell)				
Container Material		ABS (Fire-proofing ABS container available)				
Operating	Discharge	-40 ~ +60°C				
Temperature	Charge	0 ~ +40°C				
Range	Storage	-20 ~ +40°C				
	40°C / 104°F	106%				
Capacity	25°C / 77°F	100%				
Effected by Temperature	0°C / 32°F	86%				
	-20°C / -4°F	60%				
	Float Voltage	2.23V/cell@25°C,Compensation Factor: -3mV/cell/°C				
Charge Voltage	Equalize Voltage	2.35 -2.40V/cell@25°C, Compensation Factor: -3mV/cell/°C				
	Cycle Voltage	2.40 -2.50V/cell@25°C, Compensation Factor: -5mV/cell°C				
Max Charging C	urrent	60A (0.2C)				
Max. Discharge Current (5S)		1800A				
Internal Resistance		0.6mΩ				
Self Discharge		<3%, OPZV series stored at 25 ° C require a supplementary charge every six months, the charging interval would shrink when the ambient temperature went higher				

Discharge Performance

Constant Current Discharge Table (25°C/77°F) Unit: A										
	15min		1h	2h						
1.85V/cell	226	181	136	93.5	71.3	49.2	35.1	29.0	15.3	
1.80V/cell	252	200	149	99.0	74.8	51.0	36.5	30.0	15.9	
1.75V/cell	269	213	157	104	76.6	52.4	37.3	30.8	16.3	
1.70V/cell	285	225	165	107	78.3	53.6	37.8	31.2	16.5	
1.65V/cell	300	237	172	110	79.7	54.5	38.4	31.5	16.7	
1.60V/cell	316	245	179	112	80.4	55.0	38.8	31.8	16.7	

Constant Power Discharge Table (25°C/77°F) Unit: W									
F.V/Time			1h						
1.85V/cell	426	344	260	180	138	95.9	68.8	57.1	30.4
1.80V/cell	463	372	282	190	144	98.7	70.9	58.5	31.2
1.75V/cell	487	391	294	197	147	101	72.2	59.7	31.8
1.70V/cell	508	408	307	202	149	103	72.8	60.2	32.2
1.65V/cell	526	425	317	207	151	104	73.7	60.6	32.3
1.60V/cell	546	432	328	208	152	105	74.2	61.0	32.4


Motive

Energy Storage Battery


Reserve Battery

☐ Motorcycle Battery


Discharge Characteristics Curve




Cycle life in relation to depth of Discharge




Charging Characteristics Curve




Temperature effects on Capacity




Relationship between charging voltage and temperature




Temperature effects on Float life



Self-discharge Characteristics



Life Characteristics of Standby use



@2016 All right reserved by Tianneng Group; Trademarks and logos are the property of Tianneng Group and its affiliates