☐ Motive Battery





☐ Reserve Battery





Energy Storage Battery-Tubular GEL Technology-OPzV Series

OPzV350

(2V 350Ah) **GENERAL FEATURES**

- 20 years design life at floating condition
- Wide operating temperature range from -40°C to +60°C
- Tubular positive plate with prolonged cycle life
- Fumed silica gel electrolyte
- lead-calcium grid significantly improves the corrosion resistance ability
- Low self-discharge rate and long shelf life
- Excellent deep discharge recovery capability


Application

- Renewable energy system
- Hybrid solar power system
- Uninterrupted Power Supply (UPS)
- Communications and electric equipment
- Emergency lighting equipment
- Fire alarm and security systems
- Control equipment, and other factory automation equipment
- Emergency power supply (EPS)
- Lighting equipment

Dimension

Unit:mm

Length 124±2mm / 4.88inch Width 206±2mm / 8.11inch Container Height 473±3mm / 18.62inch **Total Height** 505±3mm / 19.88inch












Unit:mm

Terminal Type:

Weight

28.5kg 62.83lbs



This document is subject to change without prior notification

Motive Battery





■ Reserve Battery

■ Motorcycle Battery

OPzV350

Specificaion						
Nominal Voltag	e	2V				
		371Ah 20hr Rate(1.80V/cell)				
		350Ah 10hr Rate(1.80V/cell)				
Rated Capacity(25°C)		305Ah 5hr Rate(1.75V/cell)				
		274Ah 3hr Rate(1.70V/cell)				
		209Ah 1hr Rate(1.60V/cell)				
Container Material		ABS (Fire-proofing ABS container available)				
Operating	Discharge	-40 ~ +60°C				
Temperature	Charge	0 ~ +40°C				
Range	Storage	-20 ∼ +40°C				
	40°C / 104°F	106%				
Capacity	25°C / 77°F	100%				
Effected by Temperature	0°C / 32°F	86%				
	-20°C / -4°F	60%				
	Float Voltage	2.23V/cell@25°C,Compensation Factor: -3mV/cell/°C				
Charge Voltage	Equalize Voltage	2.35 -2.40V/cell@25°C, Compensation Factor: -3mV/cell/°C				
	Cycle Voltage	2.40 -2.50V/cell@25°C, Compensation Factor: -5mV/cell°C				
Max Charging C	Current	70A (0.2C)				
Max. Discharge	Current (5S)					
Internal Resistance		0.6mΩ				
Self Discharge		<3%, OPZV series stored at 25 ° C require a supplementary charge every six months, the charging interval would shrink when the ambient temperature went higher				

Discharge Performance

Constant Current Discharge Table (25°C/77°F) Unit: A										
F.V/Time	15min		1h							
1.85V/cell	264	211	159	109	83.2	57.4	40.9	33.9	17.9	
1.80V/cell	293	233	174	116	87.3	59.5	42.6	35.0	18.6	
1.75V/cell	313	249	183	121	89.4	61.1	43.5	35.9	19.0	
1.70V/cell	332	263	193	125	91.3	62.5	44.1	36.3	19.3	
1.65V/cell	350	277	201	128	93.0	63.5	44.8	36.7	19.4	
1.60V/cell	369	286	209	130	93.8	64.2	45.2	37.1	19.5	

Constant Power Discharge Table (25°C/77°F) Unit: W									
F.V/Time									
1.85V/cell	496	402	304	210	161	112	80.2	66.6	35.4
1.80V/cell	540	434	329	221	168	115	82.7	68.3	36.4
1.75V/cell	568	456	343	230	171	118	84.2	69.6	37.1
1.70V/cell	592	476	358	236	174	120	85.0	70.2	37.5
1.65V/cell	613	496	370	241	176	121	86.0	70.7	37.7
1.60V/cell	636	504	382	243	177	122	86.5	71.2	37.8


Motive

Energy Storage Battery


Reserve Battery

☐ Motorcycle Battery


Discharge Characteristics Curve




Cycle life in relation to depth of Discharge




Charging Characteristics Curve




Temperature effects on Capacity




Relationship between charging voltage and temperature




Temperature effects on Float life



Self-discharge Characteristics



Life Characteristics of Standby use



@2016 All right reserved by Tianneng Group; Trademarks and logos are the property of Tianneng Group and its affiliates