

Motive Battery-Deep Cycle Type-TNE Series


TNE6-250T (6V 250Ah) GENERAL FEATURES


- Oxygen recombination technology:Maintenance Free VRLA Battery, no need to add water or acid
- The patent grid alloy:less gassing, low self-discharge, excellent corrosion resistence performance
- Special paste formula: addictives are added to improve deep discharge,long cycle life
- High quality AGM separator: extend cycle life and prevent micro short circuit
- The patent Nano silica gel electrolytes, extend cycle life and improve the deep discharge performance
- ABS container: increase the strength of battery (Flame-retardant ABSUL94-V0 is optional)


Dimension

Unit:mm

Length	330±2mm	/	12.99inch
Width	180±2mm	/	7.09inch
Container Height	222±2mm	/	8.74inch
Total Height	222±2mm	1	8.74inch










icati	

- Electric tools or toys
- Electric Bicycle/Tricycle
- Golf trolleys and golf cart
- Patrol car
- Electric Sight-seeing Tour Bus
- Sweeper

Terminal

- Wheelchairs
- Lawn mowers
- Illumination light



Weight	
35kg	77.16lbs

This document is sub	ject to change with	out prior notification

Tianneng Battery Group Co., Ltd.	Changxing Tianying Import & Export Co., Ltd.	www.tiannenggroup.com	Version:	V1.1	Release Date:	2017.3.1
@2016 All right reserved by Tianneng Group; Trademarks and logos are the property of Tianneng Group and its affiliates			jiao Road, Huaxi Indu	strial Zone of (Changxing County, Zhe	jiang, China



Motive Battery

Energy Storage Battery

Reserve Battery

Specificaion

Motorcycle Battery



TNE6-250T

2.30Vpc


0.01CA

100

21 24 27

Nominal Volta	ige	6V
Nominal Capa	city	250Ah
Rated	C20(1.80V/cell)	250Ah
Capacity	C10(1.80V/cell)	230Ah
(25°C)	C5(1.75V/cell)	220Ah
Container Ma	terial	ABS (Flame-retardant ABSUL94-V0 is optional)
Operating	Discharge	-20 ~ +50°C
Temperature	Charge	0 ~ +40°C
Range	Storage	-15 ~ +40°C
Course it a	40°C / 104°F	106%
Capacity Effected by	25°C / 77°F	100%
Temperature	0°C / 32°F	86%
remperature	-10°C / 14°F	65%
Charge Method		Please refer to the "Charge Characteristics (25°C) " below
Monthly Self Discharge		<3%, TNE series stored at 25°C require a supplementary charge every six months, the charging interval would shrink when the ambient temperature went higher

Performance Curve



Tianneng Battery Group Co., Ltd.	Changxing Tianying Import & Export Co., Ltd.	www.tiannenggroup.com	Version:	V1.1	Release Date:	2017.3.1
@2016 All right reserved by Tianneng Group; Trademarks and logos are the property of Tianneng Group and its affiliates			No.18th, Baoqiao Road, Huaxi Ind	ustrial Zone	of Changxing County, Zhej	jiang, China