



Motive Battery-Deep Cycle Type-TNE Series

TNE6-270 (6V 270Ah) **GENERAL FEATURES**


- Oxygen recombination technology:Maintenance Free VRLA Battery, no need to add water or acid
- The patent grid alloy:less gassing, low self-discharge, excellent corrosion resistence performance
- Special paste formula: addictives are added to improve deep discharge, long cycle life
- High quality AGM separator: extend cycle life and prevent micro short circuit
- The patent Nano silica gel electrolytes, extend cycle life and improve the deep discharge performance
- ABS container: increase the strength of battery (Flame-retardant ABSUL94-V0 is optional)

Dimension

Unit:mm

0 +

Length	330±2mm	/	12.99inch
Width	180±2mm	/	7.09inch
Container Height	222±2mm	/	8.74inch
Total Height	222±2mm	/	8.74inch



VAR • 0

<u>'QM</u>

F



Application

- Electric tools or toys
- Electric Bicycle/Tricycle • Golf trolleys and golf cart
- Patrol car
- Electric Sight-seeing Tour Bus
- Sweeper
- Wheelchairs
- Lawn mowers
- Illumination light

Terminal	
Unit:mm	
Terminal Type: I7	

weight	
36.5kg	80.47lbs

This document is subject to change withou	t prior notification
---	----------------------

ISO9001 ISO1400	01 OHSAS18001	This document is subject to change without prior notification				
Tianneng Battery Group Co., Ltd.	Changxing Tianying Import & Export Co., Ltd.	www.tiannenggroup.com	Version:	V1.1	Release Date:	2017.3.1
@2016 All right reserved by Tianneng Group; Trademarks and logos are the property of Tianneng Group and its affiliates No.18th, Baoqiao Road, Huaxi Industrial Zone of Changxing County, Zhejiang, China					jiang, China	



Motive Battery

Energy Storage Battery

Reserve Battery

Specificaion


Motorcycle Battery



TNE6-270

Nominal Volta	ige	6V
Nominal Capacity		270Ah
Rated	C20(1.80V/cell)	270Ah
Capacity	C10(1.80V/cell)	260Ah
(25°C)	C5(1.75V/cell)	244.4Ah
Container Material		ABS (Flame-retardant ABSUL94-V0 is optional)
Operating Temperature Range	Discharge	-20 ~ +50°C
	Charge	0 ~ +40°C
	Storage	-15 ~ +40°C
C	40°C / 104°F	106%
Capacity Effected by	25°C / 77°F	100%
Temperature	0°C / 32°F	86%
remperature	-10°C / 14°F	65%
Charge Method		Please refer to the "Charge Characteristics (25°C) " below
Monthly Self Discharge		<3%, TNE series stored at 25°C require a supplementary charge every six months, the charging interval would shrink when the ambient temperature went higher

Performance Curve



Tianneng Battery Group Co., Ltd.	Changxing Tianying Import & Export Co., Ltd.	www.tiannenggroup.com	Version:	V1.1	Release Date:	2017.3.1
@2016 All right reserved by Tianneng Group; Trademarks and logos are the property of Tianneng Group and its affiliates		No.18th, Baoqiao Road, Huaxi Industrial Zone of Changxing County, Zhejiang, China				