

Energy Storage Battery



Motorcycle Battery



Motive Battery-Deep Cycle Type-TNE Series

TNE8-180A (8V 180Ah) **GENERAL FEATURES**

- Oxygen recombination technology:Maintenance Free VRLA Battery, no need to add water or acid
- The patent grid alloy:less gassing, low self-discharge, excellent corrosion resistence performance
- Special paste formula: addictives are added to improve deep discharge, long cycle life
- High quality AGM separator: extend cycle life and prevent micro short circuit
- The patent Nano silica gel electrolytes, extend cycle life and improve the deep discharge performance
- ABS container: increase the strength of battery (Flame-retardant ABSUL94-V0 is optional)

Dimension


Unit:mm

Length	262±2mm	/	10.31inch
Width	182±2mm	/	7.17inch
Container Height	280±2mm	/	11.02inch
Total Height	280±2mm	/	11.02inch



Vie

(0



Application

- Electric tools or toys
- Electric Bicycle/Tricycle
- Golf trolleys and golf cart
- Patrol car
- Electric Sight-seeing Tour Bus
- Sweeper

Terminal

- Wheelchairs
- Lawn mowers
- Illumination light

Unit:mm Terminal Type:	I7
	3

Weight	
33.5kg	73.85lbs

0

ISO9001

@2016 All right res

CE

1	ISO14001	OHSAS18001		, ,	J		
Group	Co., Ltd.	Changxing Tianying Import & Export Co., Ltd.	www.tiannenggroup.com	Version:	V1.1	Release Date:	2017.3.1
eserved	d by Tianneng	Group; Trademarks and logos are the property of Tianneng Grou	up and its affiliates No.18th, Baoq	iao Road, Huaxi Indu	strial Zone of	Changxing County, Zhej	iang, China



Motive Battery

Energy Storage Battery

Reserve Battery

Specificaion

Motorcycle Battery



TNE8-180A

2.30Vpc

0.01CA

10℃

S6≤4h

21 24 27

Nominal Voltage		8V
Nominal Capacity		180Ah
Rated	C20(1.80V/cell)	180Ah
Capacity	C10(1.80V/cell)	170Ah
(25°C)	C5(1.75V/cell)	160Ah
Container Ma	terial	ABS (Flame-retardant ABSUL94-V0 is optional)
Operating	Discharge	-20 ~ +50°C
Temperature	Charge	0 ~ +40°C
Range	Storage	-15 ~ +40°C
Como di ta	40°C / 104°F	106%
Capacity Effected by	25°C / 77°F	100%
Temperature	0°C / 32°F	86%
remperature	-10°C / 14°F	65%
Charge Method		Please refer to the "Charge Characteristics (25°C) " below
Monthly Self Discharge		<3%, TNE series stored at 25°C require a supplementary charge every six months, the charging interval would shrink when the ambient temperature went higher

Performance Curve



Tianneng Battery Group Co., Ltd.	Changxing Tianying Import & Export Co., Ltd.	www.tiannenggroup.com	Version:	V1.1	Release Date:	2017.3.1
@2016 All right reserved by Tianneng Group; Trademarks and logos are the property of Tianneng Group and its affiliates			No.18th, Baoqiao Road, Huaxi Ind	lustrial Zone	of Changxing County, Zheji	iang, China